





		र्ग	マライトの上のスポッ	٢		
ドット %	L*	a*	b*	C*	h°	TVI
0	93.05	-0.18	0.13	0.22	143.91	0%
10	91.24	1.13	3.22	3.41	70.70	9%
20	90.34	1.76	4.41	4.75	68.25	12%
30	89.02	2.64	6.16	6.70	66.79	16%
40	87.22	3.91	8.78	9.61	66.00	20%
50	84.59	5.65	12.37	13.60	65.46	28%
60	81.53	7.48	15.94	17.60	64.87	47%
70	77.50	9.70	20.11	22.33	64.24	63%
80	72.99	11.85	24.11	26.86	63.82	79%
90	69.49	13.29	26.68	29.80	63.52	90%
100	64.42	14.99	29.86	33.42	63.35	100%

	仕様
不透明度(Y 比率)	2%
スペクトル密度	1.28
ドットゲイン @ 50%	-22%
コントラスト @ 70%	12%
	測定値
測定器	i1iO 2
701-th . =	
測定コンディション	, 2_Degree,
測定コンテインヨンジオメトリ	, 2_Degree, 0.0/45.0





